

KA Unbleached Kraft Paper

The Certificate of Quality

Minimal /Typical Values (STO 80241670-001-2015)

Property	Grades											Method
	K-100	K-110	K-115	K-125	K-135	K-140	K-150	K-165	K-175	K-200	K-220	
Substance, g/m² Maximum permissible deviation $\pm$ 3%	100	110	115	125	135	140	150	165	175	200	220	ISO 536
Bursting Strength, kPa	420-450	460-490	500-530	530-560	560-590	580-610	600-630	620-650	640-670	680-710	700-730	ISO 2759
SCT (CD), kN/m	1,7-1,8	1,9-2,0	2,1-2,2	2,2-2,3	2,3-2,4	2,4-2,6	2,8--2,9	3,0-3,1	3,2-3,3	3,5-3,7	3,7-3,9	ISO 9895
RCT, N, min.	115	125	130	150	160	170	190	200	220	250	260	
Cobb test; 60 sec., g/m² -top	35	35	35	35	35	35	35	35	35	35	35	ISO 535
Moisture, %	6-10	6-10	6-10	6-10	6-10	6-10	6-10	6-10	6-10	6-10	6-10	ISO 287

100/125/140/175gsm in stock.

For further enquiries, please contact us.